



# Welded Beams and Columns AS/NZS 3679.2 – 300 (L15)

## General description

- Welded Beams and Columns are manufactured in accordance with AS/NZS 3679.2:2016, from plate manufactured to AS/NZS 3678:2016 with a nominal yield strength of 300MPa. 300L15 has a guaranteed impact performance at -15°C.

## Typical uses

- Heavier end of the engineering construction, buildings, mining infrastructure and transport market in applications such as office buildings, shopping centres, stadiums, car parks and bridges.

## Features & benefits

- Consistent, uniform deep penetration fillet weld profile
- Guaranteed minimum strength levels
- Low temperature properties (if specified)
- ACRS accreditation (ACRS Certificate No. 120802)
- ATIC10 accreditation

## Warnings

This material should be used in conjunction with the appropriate structural design and welding standards.  
Maximum recommended temperature for hot forming is 620°C. If heated above 620°C, mechanical properties may deteriorate.

## Australian and International Standards

AS/NZS 3678:2016  
AS/NZS 1365:1996 (R2016)  
AS/NZS 3679.2:2016  
ISO 9001:2015 Quality System Certified

## Supply conditions

	Normal	Optional
Plate Thickness Range	10 – 40 mm	-
Plate Tolerances	AS/NZS 1365:1996 (R2016)	-
Beam Tolerances	AS/NZS 3679.2:2016	-
Ultrasonic Inspection	-	AS 1710-2007 (R2017)
Surface Inspection	BlueScope	-
Certification	BlueScope	-

## Tensile test requirements for welded web-to-flange test

Grade to AS/NZS 3678:2016	Specified Minimum Tensile Strength (MPa)	Nominal Thickness of Web (mm)	Minimum test load per unit flange/web length (kN/mm)
300	430	10	4.30
		12	5.16
		≥ 16	6.88

### Charpy impact properties

Charpy Impact Properties	Longitudinal on 10 X 10 mm test piece	Test Temperature (°C)	Absorbed Energy (joules)	
			Avg. of 3	Individual
Guaranteed Min	300L15	-15	27	20

### Fire hazard properties

Test & Evaluation Method	Result
Combustibility test for materials (AS 1530.1-1994 (R2016))	Not deemed combustible

**steel.com.au**

To ensure you have the most current Data Sheet

**1800 024 402**

[steeldirect@bluescopesteel.com](mailto:steeldirect@bluescopesteel.com)

For more information contact Steel Direct



The information contained in this datasheet is provided by way of general information about this product only, and has not been prepared with your specific needs in mind. We recommend that you seek BlueScope's advice as to the suitability of this product for the purpose(s) for which you propose to use it. To contact BlueScope for advice about your proposed use of this product, please contact Steel Direct. BlueScope and the BlueScope brand mark are registered trade marks of BlueScope Steel Limited.

© 2020 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved