

Coated Steel – Prepainted Data Sheet



December 2017. This literature supersedes all previous issues

COLORBOND® XHI steel

General description

COLORBOND® XHI (Exterior Home Improvement) prepainted steel has been specifically designed by BlueScope to provide a high durability material for patios and pergolas, generally with a high gloss finish. A standard gloss finish is also available.

Typical uses

Patios, carports and pergolas. Typically used for roofing, post and beam components. To determine if warranties apply or for material selection advice, please visit colorbond.com and steel.com.au or contact Steel Direct for advice.

Australian and International standards

Substrate - AS 1397
Paint Coating- AS/NZS 2728 Type 4
ISO 9001 Quality System certified

Preferred substrates

AM100 G300S & G550S steel with Activate® technology. Z275 G300S & G550S steel {Refer Note 9}.

For substrate properties please refer to the relevant Metallic (AM and Z) Coated steel datasheets or AS1397.

Please refer to current price list or BlueScope State Sales Office for availability of colours and dimensions.

CORSTRIP® protective film may be available on request {Refer Note 4}



Attributes tested during manufacture

Property	Test & Evaluation Method(s)	Results
Adhesion		
Reverse Impact	AS/NZS 2728 (App. E)	≥10 joules
T-bend	AS/NZS 2728 (App. F)	Maximum 6T. Refer Note 8.
Hardness		
Pencil	AS1580.405.1	HB or harder
Specular gloss		
60° meter	AS/NZS 1580 602.2; ASTM D523	≥70 units for nominal 80 gloss product. Otherwise Nominal ± 10 units

Product Attributes

Property	Test & Evaluation Method(s)	Results
Flexibility		
T-bend	ASTM D4145	Maximum 10T (no cracking). Refer Note 8.
Resistance to abrasion		
Scratch	AS/NZS 2331.4.7	Typically 2000g
Adhesion		
Natural well washed exposure (10 yrs)	AS/NZS 1580.457.1	No flaking or peeling. Refer Notes 10 & 11.
Resistance to humidity		
Cleveland (500 hours)	ASTM D4585; AS/NZS 1580.481.1.9 (Blisters); AS/NZS 1580.408.4 (Adhesion)	Blister density: ≤ 3 . Blister size: $\leq S2$. No loss of adhesion or corrosion.
Resistance to corrosion		
QFog (2000 hours)	AS/NZS 1580.481.1.9 (Blisters); AS1580.408.4 (Adhesion), AS1580.481.3 (undercutting, Corrosion)	Blister density: ≤ 2 . Blister size: $\leq S2$. Undercut from score: ≤ 1 mm. No loss of adhesion or corrosion of base metal. Refer Note 3.
Resistance to colour change		
Natural well washed exposure (10 yrs)	AS/NZS 1580.457.1 & ASTM D2244 (Colour)	ΔE CIElab 2000: Light colour: ≤ 4 units. Intermediate colour: ≤ 6 units. Dark colour: ≤ 10 units. Refer Notes 10 & 11.
QUV (2000 hours)	ASTM G154 & ASTM D2244 (Colour)	ΔE CIElab 2000: Intermediate colour: ≤ 5 units.
Resistance to chalking		
Natural well washed exposure (10 yrs)	AS/NZS 1580.457.1 & AS/NZS 1580.481.1.11 (Chalk Method B)	Chalk rating: ≤ 4 . Refer Notes 10 & 11.
QUV (2000 hours)	ASTM G154 & AS/NZS 1580.481.1.11 (Chalk Method B)	Chalk rating: ≤ 4 .
Resistance to solvents, acids, alkalis		
Exposure	ASTM D1308 (3.1.1); ASTM D2244 (Colour); AS/NZS 1580.481.1.9 (Blisters)	No discolouration or blistering. Refer Notes 3, 10 & 12.
Resistance to fire		
Fire test performance	AS/NZS 1530.3	Ignitability index: 0 rating in scale of 0-20 Spread of flame index: 0 rating in scale of 1-10 Heat evolved index: 0 rating in scale of 0-10 Smoke developed index: 2 rating in scale of 0-10.
NCC Non-Combustible Material Deemed-to-Satisfy Provisions	National Construction Code, Building Code of Australia Volume 1 Part C1.12.e, and Volume 2: Part 3.7.1.2.e	May be used wherever a non-combustible material is required.
Resistance to heat		
Exposure 100°C continuous (500 hrs)	ASTM D2244 (Colour)	Colour change: ΔE CIElab 2000: ≤ 3 units.

Important notes

1. When the Backing Coat side of roof sheets are exposed to the weather because the High Gloss Finish Coat is needed in a finished ceiling type application, it could result in the Backing Coat prematurely weathering. Depending on the design of the structure, for the homeowner this may be an acceptable outcome eg for flat patios, where the top side is not visible. Alternately, COLORBOND® XHI steel can be ordered with a Finish Coat on both sides for such applications where both the top and bottom sides of the sheets will be visible and where appearance is critical.
2. All warranties for a product, if any, are subject to eligibility. Terms and conditions apply. Nothing in this document is intended by BlueScope to extend, modify or otherwise affect any stated product warranty. To find out more, please visit the BlueScope website or contact Steel Direct for advice.
3. Product may not be suitable if it is intended to use COLORBOND® XHI steel in an exterior application within 1km of salt marine locations, severe industrial or abnormally corrosive environments; in areas not washed by rain, or in applications where it will be wholly or partly buried in the ground. For selection of the most appropriate COLORBOND® steel product, please refer to Technical Bulletins TB1a, TB1b, CTB16, CTB21 and CTB22. Before purchase, you should check on suitability by visiting the BlueScope website or by contacting Steel Direct for advice.
4. The CORSTRIP® protective film should be removed from the painted steel strip immediately on installation. Sunlight can increase adhesion of the protective film to the painted surface if left uncovered outside.
5. Finish Coat - the coating applied to the exposed surface of the prepainted coil which is expected to meet the Performance Requirements.
6. The product is generally supplied with a nominal 80 unit (60°) gloss Finish Coat.
7. Backing Coat - a thin coating applied to the reverse surface of the prepainted coil. It also gives additional durability to the reverse surface during the service life of the product, but for aesthetic reasons is not recommended for exposure to sunlight. Performance Requirements are generally not applicable to backing coats. Where specific Performance Requirements are deemed necessary for the reverse surface coating, a "double sided" product should be specified, in which case a topcoat of full nominal thickness will be applied.
8. The minimum internal bend diameters for forming processes to achieve no paint cracking (visible using x10 magnification) and to avoid paint adhesion issues are specified by the T-bend flexibility and T-bend adhesion results respectively- where 1T equals the total coated thickness (tct) in mm of the material. These results are based on testing at 20-25°C.
9. For most products, the metallurgical ageing process which is inherent in the paint stoving cycle will result in some loss of ductility compared with unpainted product. However, minimum strength levels designated by relevant standards will still be applicable.
10. Improper storage or use of non-approved roll-forming lubricants may cause brand transfer and paint blushing, and may adversely affect colour and long term durability. Product in coil or sheet pack form must be kept dry. If the coil or sheet pack becomes wet, it must be separated and dried (refer AS/NZS 2728 Appendix L, and also Technical Bulletin TB7). Contact Steel Direct to obtain advice on appropriate rollforming lubricants.
11. Values quoted are for panels exposed in accordance with AS/NZS 2728. Variations for in-situ performance may occur due to complexity of building design and location.
12. COLORBOND® XHI steel has good resistance to accidental spillage of solvents such as methylated spirits, white spirit, mineral turpentine, toluene, trichloroethylene and dilute mineral acids and alkalis. However, all spillages should be immediately removed by water washing and drying.

Colorbond®

colorbond.com
steel.com.au

To learn more about this product

1800 022 999

For more information call Steel Direct

