

Contact with timber

Green or unseasoned timber should not come into contact with COLORBOND® prepainted steel, ZINCALUME® aluminium/zinc/magnesium alloy-coated steel, TRUECORE® aluminium/zinc/magnesium alloy-coated steel or zinc-coated steel due to acidic substances in the timber which have a corrosive effect on the metallic coating. The use of kiln dried or appropriate dried timber species is therefore recommended for any situation where intimate contact between the metallic coated steel and timber is considered.

NOTE: Testing has shown that increased time of wetness is a major contributor to the accelerated corrosion of metallic coated steel when placed in contact with timber. As such, galvanised steel, COLORBOND® steel, ZINCALUME® steel and TRUECORE® steel must not be placed in contact with green/unseasoned timbers or timbers that are likely to retain moisture as a result of the surrounding environment.

Some preservative treatments for wood can have an adverse effect on the metallic coated steel with which it is in contact. Timber treated with some preservatives can be severely corrosive to the majority of the metallic building components. The presence of soluble salts (e.g. sodium sulphate) derived from the treatment process, will contribute to the corrosion mechanism by increasing ionic conductivity. The

time of wetness of the metal surface contributes to the overall corrosion mechanism. Corrosion of metals (i.e. fasteners) embedded in timber is known to take place when the timber moisture content exceeds 17% moisture. This situation is likely to occur as a result of humid tropical environments leading to entrapped condensation (i.e. wet timber). It can also arise from substandard detailing during construction, green/unseasoned timber or timber which is constantly moist.

Treated timber cladding used in a run-off situation, can result in a corrosive leachate from the timber which, if it contacts COLORBOND® steel, ZINCALUME® steel, TRUECORE® steel, or zinc-coated steel will promote corrosion. BlueScope specifically recommend against the use of treated timbers of this type for high moisture situations such as roof and ceiling battens, composite fence constructions and built up flooring or external decking which may utilise a metallic coated steel structural support system. If treated timbers must be used, then the timber and/or steelwork should be sealed by fully painting the material prior to installation.

NOTE: There are a large number of treated timbers available and as such BlueScope are not in a position to comprehensively test all timbers. Therefore, BlueScope are unable to advise of the suitability for the use with BlueScope steel products and would recommend against their use unless the timber treatment is examined closely for possible detrimental effects on metallic coupled items prior to general specification and application of the material.

Nail plates are commonly used to fabricate wooden truss components. BlueScope recommend that the timber must be seasoned or kiln dried prior to use. Some end use environments will require the use of heavier coating mass or more corrosion resistant coatings to prevent long term degradation.

Figure 1: Corrosion resulting from contact of treated timber with zinc-coated steel purlins.



steel.com.au

To ensure you have the most current Technical Bulletin

1800 800 789

steeldirect@bluescopesteel.com

If you have any questions regarding this Bulletin, contact Steel Direct



BLUESCOPE

The information and advice contained in this Technical Bulletin ('Bulletin') is of a general nature only and has not been prepared with your specific needs in mind. You should always obtain specialist advice to ensure that the materials, approach and techniques referred to in this Bulletin meet your specific requirements. BlueScope Steel Limited makes no warranty as to the accuracy, completeness or reliability of any estimates, opinions or other information contained in this Bulletin and to the maximum extent permitted by law, BlueScope Steel Limited disclaims all liability and responsibility for any loss or damage, direct or indirect, which may be suffered by any person acting in reliance on anything contained in or omitted from this Bulletin. COLORBOND®, ZINCALUME®, TRUECORE®, BlueScope and the BlueScope brand mark are registered trademarks of BlueScope Steel Limited. © 2019 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved