
Special Service Environments: Enclosed swimming pool buildings

The environment associated with an enclosed swimming pool is often found to be exceptionally severe. The severity of the environment is related to the building ventilation, temperature of the pool, proximity of the walling and roofing to the pool surface, type of chemical treatment and the duty cycle of the environment. While many municipal pool buildings are designed with appropriate ventilation capacity or often airconditioned, it has been found that during service the ventilation is reduced or the air conditioning strictly controlled to reduce operating costs. This can only increase condensation on un-insulated roof and wall sheeting leading to increased time of wetness and severe corrosion of a wide range of metallic coating types. The use of perforated ceiling systems to reduce reflected sound has been

found to increase corrosion of structural steelwork and roof sheeting located within the adjacent ceiling cavity. Condensation passes freely through the perforated ceiling tiles and condenses either on the roof sheeting or upon ineffectively installed reflective foil insulation barriers. When combined reflective foil barrier/bulk insulation are used in a pool area or other high condensation environments, great care must be taken to completely seal the lapped foil membrane with duct tape at each join. This must be carefully undertaken to prevent the penetration of moisture which will ultimately lead to corrosion of the roof sheeting and supporting structural steel work. It has been noted that when following trades have caused disruption to the foil or other barriers, and the disruption has not been adequately repaired, saturation of the

bulk wool insulation or ponding of the moisture directly upon the reflective foil barrier has occurred. This has led to accelerated corrosion of the structural roof components and perforation of the roof sheeting. Moisture will also freely penetrate plaster board sheeting and lead to similar rates of corrosion within the ceiling space. Where structural steel decking (DECKFORM® steel) is included in the building design as intermediate floors, penetration of condensation to the structural decking surface can lead to accelerated attack. Post painting of the galvanised steel surface is effective in combating such corrosive attack. Due to the variability in both design and operating parameters of enclosed pool structures, BlueScope only recommend the use of COLORBOND® Stainless steel for the cladding of pool enclosures.

steel.com.au

To ensure you have the most current Technical Bulletin

1800 800 789

steeldirect@bluescopesteel.com

If you have any questions regarding this Bulletin, contact Steel Direct



The information and advice contained in this Technical Bulletin ('Bulletin') is of a general nature only and has not been prepared with your specific needs in mind. You should always obtain specialist advice to ensure that the materials, approach and techniques referred to in this Bulletin meet your specific requirements. BlueScope Steel Limited makes no warranty as to the accuracy, completeness or reliability of any estimates, opinions or other information contained in this Bulletin and to the maximum extent permitted by law, BlueScope Steel Limited disclaims all liability and responsibility for any loss or damage, direct or indirect, which may be suffered by any person acting in reliance on anything contained in or omitted from this Bulletin. BlueScope, DECKFORM®, COLORBOND® and the BlueScope brand mark are registered trademarks of BlueScope Steel Limited. © 2019 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved.
