

# Coated Steel – Metallic

## Data Sheet



December 2017. This literature supersedes all previous issues

# GALVSPAN<sup>®</sup> steel

## G550



### General Description

GALVSPAN<sup>®</sup> G550 steel is a hot-dipped zinc-coated structural steel with a spangled surface and guaranteed minimum yield strength of 550MPa. Suitable for roll forming to a minimum internal diameter of 4t.

### Typical uses

Roll-formed sections for structural applications.

### Australian and International Standards

AS/NZS 1365:1996

AS 1397:2011

ISO 9001 Quality System certified

### Guaranteed properties of steel base

Mechanical properties	Guaranteed minimum
Yield Strength, MPa (longitudinal tensile)	550
Tensile Strength, MPa (longitudinal tensile)	550
Elongation on 80mm ( $\geq 0.60$ mm) %	2

### Chemical composition of steel base

Chemical properties	Guaranteed maximum %
Carbon - C	0.20
Manganese - Mn	1.20
Phosphorus - P	0.040
Sulphur - S	0.030

### Metal coating adhesion – 180° bend test

Coating class	Result
Z350	2t
Z450	2t

Where t = the diameter of mandrel in terms of thickness of product.

### Dimensional capabilities

Thickness range (mm)	Width range (mm)
0.30 – 0.319	800 - 1000
0.32 – 0.349	800 - 1100
0.35 – 0.399	800 - 1220
0.40 – 0.499	700 - 1220
0.50 – 0.699	700 - 1250
0.70 – 1.000	700 - 1525

Notes: Not every combination of thickness and width may be available. Supply conditions may be subject to dimensional restrictions and are subject to BlueScope Sales and Marketing confirmation. Slitting and shearing available on request from BlueScope Sales Offices. For requirements outside the standard product range please contact your local Sales Office. To determine maximum mill edge width available, subtract 30mm from the maximum width.

## Resistance to fire

Index	Range	Result
Ignitability Index	0 - 20	0
Spread of Flame Index	0 - 10	0
Heat Evolved Index	0 - 10	0
Smoke Developed Index	0 - 10	0
National Construction Code	Non-Combustible Material *	

\*According to National Construction Code, Building Code of Australia, Volume1: Part C1.12.e, and Volume 2: Part 3.7.1.2.e

## Supply conditions

Attribute	Normal	Optional
Coating Class	Z350	Z450
Surface Condition	Spangled	-
Surface Treatment	Passivated	-
Branding	Branded	-
Tolerance - Dimensions	Class A	-
Tolerance - Flatness	Class A	-

Important Notes: Optional supply conditions may be subject to dimensional restrictions

## Fabricating performance

Method	Rating
Bending	1
Drawing	NR
Pressing	NR
Roll Forming	3
Welding (design must allow for some strength reduction near welds)	5
Painting (Pre-treatment)	5

Where: 1 = Limited to 5 = Excellent or NR = Not Recommended

The ratings in this table are general indicators only, given as a guide to fabricating performance.

## Important information

Material should be used promptly (within six months) to avoid the possibility of a storage related corrosion. For selection of the most appropriate metallic coated steel, please refer to technical bulletins TB1a, TB1b, CTB21 and CTB22. For storage, rollforming lubricants and other information please refer to the Technical Bulletins.

Galvaspan®

steel.com.au

To learn more about this product

1800 064 384

For more information call Steel Direct



The information contained in this datasheet is provided by way of general information about this product only, and has not been prepared with your specific needs in mind. We recommend that you seek BlueScope's advice as to the suitability of this product for the purpose(s) for which you propose to use it. To contact BlueScope for advice about your proposed use of this product, please contact Steel Direct. GALVASPAN®, BlueScope and the BlueScope brand mark are registered trade marks of BlueScope Steel Limited.

© 2017 BlueScope Steel Limited ABN 16 000 011 058.