



# XLERPLATE<sup>®</sup> steel

## AS/NZS 3678 – A1006

### General description

A low carbon steel

### Typical uses

- Galvanising kettles

### Features & benefits

- Excellent galvanising characteristics
- Excellent weldability
- Excellent formability

### Warnings

- This material should be used in conjunction with the appropriate structural design and welding standards
- An untrimmed (mill) edge may contain surface discontinuities associated with the rolling process (refer to clause 8 of AS/NZS 3678). The plate supplied may include an amount outside of the nominal ordered width, in

accordance with relevant Australian standards. The area of the supplied plate which is outside of the nominal (customer ordered) width must not be used. Customers are advised to remove an equal width from each side of the plate when trimming.

- Correct selection of electrodes for end use application, particularly regarding galvanising tank applications, it is important to refer to electrode manufacturer

### Australian standards

AS/NZS 3678: 2016

AS/NZS 1365: 1996

ISO 9001:2015 Quality System certified

### Normal / optional supply conditions

	Normal	Optional
Thickness Range	8mm – 180mm	-
Availability	By enquiry only	-
Edge Condition	Untrimmed (Mill Edge)*	Trimmed
Tolerances	AS/NZS 1365: 1996	-
Ultrasonic Inspection	-	AS 1710: 2007
Surface Inspection	BlueScope	Third party
Certification	BlueScope	Third party endorsed

Optional supply conditions may be subject to dimensional restrictions

## Chemical composition

Element	Guaranteed Maximum %
Carbon	0.08
Silicon	0.03
Manganese	0.40
Phosphorus	0.040
Sulfur	0.030
Chromium	0.25
Nickel	0.50
Copper	0.40
Molybdenum	0.10
Aluminium	0.10
Titanium	0.040
CEQ (IIW)	0.09

All values shown refer to the relevant Australian Standard unless otherwise stated

$$CEQ(IIW) = C + \frac{Mn}{6} + \frac{(Cr + Mo + V)}{5} + \frac{(Cu + Ni)}{15}$$

**steel.com.au**

Please ensure you have the correct data sheet for this product as displayed at [www.steel.com.au](http://www.steel.com.au)

**1800 024 402**

[steeldirect@bluescopesteel.com](mailto:steeldirect@bluescopesteel.com)

For more information contact Steel Direct



The information contained in this datasheet is provided by way of general information about this product only, and has not been prepared with your specific needs in mind. We recommend that you seek BlueScope's advice as to the suitability of this product for the purpose(s) for which you propose to use it. To contact BlueScope for advice about your proposed use of this product, please contact Steel Direct. XLERPLATE®, BlueScope and the BlueScope brand mark are registered trade marks of BlueScope Steel Limited. © 2019 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved.