



XLERPLATE[®] steel

SA/AS 1548 – PT490N (L20, L40, L50)

General description

A fully killed, fine grained, carbon-manganese steel for boiler and pressure vessel applications, with a guaranteed minimum tensile strength of 490MPa. Produced by hot rolling and normalising

Features & benefits

- Grades with elevated temperature properties available
- Grades available with guaranteed low temperature properties
- Excellent weldability
- Excellent formability
- This grade is recognised in the ASME material codes

Warnings

- This material should be used in conjunction with the appropriate pressure vessel design and welding standards
- Guidelines for cold bending, where fracture toughness is important are given in AS 4100:1998 and AS 1210:2010.

Australian standards

AS 1548:2008
AS/NZS 1365:1996
ISO 9001:2015 Quality System certified

Normal / optional supply conditions

	Normal	Optional
Thickness Range	PT490N: 10mm – 100mm PT490NL20: 10mm – 100mm PT490NL40: 10mm – 80mm PT490NL50: 10mm – 80mm	-
Availability	By enquiry only	-
Edge Condition	Trimmed	-
Tolerances	Thickness : AS1548:2008 Others : AS/NZS 1365:1996	-
Ultrasonic Inspection	-	AS 1710:2007
Surface Inspection	BlueScope	Third party
Certification	BlueScope	Third party endorsed

Optional supply conditions may be subject to dimensional restrictions

Chemical composition

Element	Guaranteed Maximum %
Carbon	0.20
Silicon	0.6
Manganese	1.70
Phosphorus	0.040
Sulfur	0.030
Chromium	0.25
Nickel	0.50
Copper	0.40
Molybdenum	0.10
Aluminium	0.10
Niobium	0.050
Titanium	0.040
CEQ (IIW)	0.46

All values shown refer to the relevant Australian Standard unless otherwise stated

$$CEQ(IIW) = C + \frac{Mn}{6} + \frac{(Cr + Mo + V)}{5} + \frac{(Cu + Ni)}{15}$$

Mechanical properties

Tensile Properties (Transverse)		Thickness (mm)			
		t ≤ 16	16 < t ≤ 40	40 < t ≤ 80	80 < t ≤ 100
Yield Strength (MPa)	Guaranteed Min	360	340	330	320
Tensile Strength (MPa)	Required	490 to 610	490 to 610	490 to 610	490 to 610
Elongation 5.65√S ₀ (%)	Guaranteed Min	20	20	20	20

Charpy Impact Properties	Longitudinal on 10 X 10 mm test piece	Test Temperature (°C)	Absorbed Energy (joules)	
			Avg. of 3	Individual
Guaranteed Min	490N	0	55	43
Guaranteed Min	490NL20	-20	55	43
Guaranteed Min	490NL40	-40	45	33
Guaranteed Min	490NL50	-50	42	31

Formability	Thickness (mm)	Longitudinal	Transverse
Recommended min inside Radius	t ≤ 20	3.0t	2.0t
	20 < t ≤ 50	6.0t	4.0t
	t > 50	Hot Forming	

steel.com.au

Please ensure you have the correct data sheet for this product as displayed at www.steel.com.au

1800 024 402

steeldirect@bluescopesteel.com

For more information contact Steel Direct



The information contained in this datasheet is provided by way of general information about this product only, and has not been prepared with your specific needs in mind. We recommend that you seek BlueScope's advice as to the suitability of this product for the purpose(s) for which you propose to use it. To contact BlueScope for advice about your proposed use of this product, please contact Steel Direct. XLERPLATE®, BlueScope and the BlueScope brand mark are registered trade marks of BlueScope Steel Limited. © 2019 BlueScope Steel Limited ABN 16 000 011 058. All rights reserved.