# **Coated Steel - Metallic**

**Data Sheet** 

August 2019. This literature supersedes all previous issues



# ZINC HI-TEN® steel G500 / G500S

### **General Description**

ZINC HI-TEN® G500 steel is a hot-dipped zinccoated structural steel with a spangled surface and guaranteed minimum yield strength of 500MPa. Suitable for roll-forming to a 4t minimum internal diameter.

ZINC HI-TEN® G500S steel is skin passed to improve surface quality.

### Typical uses

Structural sections, house framing, agricultural posts and trellises.

# **Australian and International Standards**

AS/NSZ 1365: 1996 AS 1397:2011 ISO 9001:2015 Quality System certified

Guaranteed properties of steel base

Mechanical properties	Guaranteed minimum	
Yield Strength, MPa (longitudinal tensile)	500	
Tensile Strength, MPa (longitudinal tensile)	520	
Elongation on 80mm (≥ 0.60mm) %	7	
180° Transverse Bend	6t	

## Chemical composition of steel base

Chemical properties	Guaranteed maximum %
Carbon - C	0.20
Manganese - Mn	1.20
Phosphorus - P	0.040
Sulphur - S	0.030

Metal coating adhesion - 180° bend test

Coating class	Result
Z100	1t
Z200	2t
Z275	2t
Z450	2t
Z600	3t

Where t = the diameter of mandrel in terms of thickness of product.

**Dimensional capabilities** 

Thickness range (mm)	Width range (mm)
1.001 – 1.499	700 - 1525

Notes: Not every combination of thickness and width may be available. Supply conditions may be subject to dimensional restrictions and are subject to BlueScope Sales and Marketing confirmation. Slitting and shearing available on request from BlueScope Sales Offices. For requirements outside the standard product range please contact your local Sales Office. To determine maximum mill edge width available, subtract 30mm from the maximum width.

Fire hazard properties

File flazard properties		
Test & Evaluation Methods	Range	Result
Simultaneous determination of ignitability, flame propagation, heat release and smoke release (AS/NZS 1530.3:1999)	Ignitability Index (0 – 20)	0
	Spread of Flame Index (0 – 10)	0
	Heat Evolved Index (0 – 10)	0
	Smoke Developed Index (0 – 10)	2
NCC non-combustible material concessions (NCC 2019; AS/NZS 1530.3:1999)	National Construction Code, Building Code of Australia 2019; Volume 1: Part C1.9.e, and Volume 2: Part 3.7.1.1.e	May be used wherever a non-combustible material is required
	AS/NZS 1530.3:1999	
Combustibility test for materials (steel substrate) (AS 1530.1-1994)	AS 1530.1-1994	Not deemed combustible (steel substrate)

Supply conditions

Attribute	Normal	Optional
Coating Class	Z275	Z200, Z450, Z600
Surface Condition	Spangled	Minimised Spangle
Surface Treatment	Passivated	1
Branding	Branded	-
Tolerance - Dimensions	Class A	
Tolerance - Flatness	Class A	-

Important Notes: Optional supply conditions may be subject to dimensional restrictions.

**Fabricating performance** 

Method	Rating
Bending	2
Drawing	NR
Pressing	NR
Roll Forming	3
Welding (design must allow for some strength reduction near welds)	5
Painting Pre-treatment	5

Where: 1 = Limited to 5 = Excellent or NR = Not Recommended

The ratings in this table are general indicators only, given as a guide to fabricating performance.

### Important information

Skin-passing will generally give a marginally higher yield strength and marginally reduced % elongation. Material should be used promptly (within six months) to avoid the possibility of a storage related corrosion. For selection of the most appropriate metallic coated steel, please refer to technical bulletins TB1a, TB1b, CTB21 and CTB22. For storage, rollforming lubricants and other information please refer to the Technical Bulletins.

steel.com.au

To learn more about this product

1800 064 384

steeldirect@bluescopesteel.com
For more information contact Steel Direct



